

KGT 264 is a high Density polyethylene with Butene-1 as comonomer. It is a high molar mass for blown. The product has good toughness, low gel level and good tear strength.

Applications

- Food Grade
- Blown film with paper like quality
- Suitable for counter bags
- Carrier bags
- Wrapping film and sheets
- Blending partner

Stabilization

- Ca-Stearate
- Zn-Stearate
- Irgafos168

Resin properties	Typical Value	Unit	Test Method
Physical			
Melt flow rate (190°C/5Kg)	0.28 ± 0.07	g/10min	ISO 1133
Melt Flow Rate (190°C/2.16Kg)	8.0 ± 2.0	g/10min	ISO 1133
Density	0.949 ± 0.002	g/cm ³	ISO 1183
FRR21.6/5	30 ± 4	-----	-----