

KGT is able to produce all grades of road bitumen in accordance with national standards.

The experiment	Limit	Test Method
Specific Gravity	1.00-1.25	ASTM D3289
penetration (@25 °C,100g,5s),0.1mm	60-90	ASTM D5
Softening point, °C	40-60	ASTM D36
Ductility Point (@25 °C,5cm/min),cm	min 100	ASTM D113
Loss on heating, wt%	max 0.03	ASTM D6
Flash point	min 230	ASTM D92
Solubility in TCE, wt%	min 99.0	ASTM D4
Spot test	Negative	AASHTO T102